

## TECHNICAL SPECIFICATION

Reference **ASG - 1000**

Descripción **Vetrosa Grit**

### CHEMICAL COMPOSITION

SiO <sub>2</sub> 71,00 ± 1,50	RO 2,00 ± 0,50	R2O 7,00 ± 1,00
R2O3 20,00 ± 1,00		

### PHYSICAL FEATURES

Maximum humidity **0,00 %**

Particle Size

> 160 μm	1,00 ± 0,50
> 90 μm	40,00 ± 5,00
> 45 μm	50,00 ± 5,00
< 45 μm	10,00 ± 3,00

Coefficient of Expansion **52x10<sup>-7</sup>**

Softening Point **805 °C**

Presentation **Grit**

### Use

Range T<sup>a</sup> **1000 - 1040 °C**

Use **Exclusive use for ceramics**