

TECHNICAL SPECIFICATION

Reference **ASG - 1020**

Description **Vetrosa Grit**

CHEMICAL COMPOSITION

SiO ₂ 72,00 ± 1,50	RO 3,00 ± 0,50	R2O 9,00 ± 1,00
R2O3 16,00 ± 1,00		

PHYSICAL FEATURES

Maximum humidity **0,00 %**

Particle Size

> 212 μm	1,00 ± 0,50
> 90 μm	70,00 ± 5,00
> 45 μm	25,00 ± 5,00
< 45 μm	7,00 ± 3,00

Coefficient of Expansion **56x10⁻⁷**

Softening Point **840 °C**

Presentation **Grit**

Use

Range T^a **1000 - 1080 °C**

Use **Exclusive use for ceramics**