

## TECHNICAL SPECIFICATION

Reference

**ASG - 1031**

Descripción

**Vetrosa Grit**

### CHEMICAL COMPOSITION

**SiO<sub>2</sub> 72,50 ± 1,50**

**RO 2,50 ± 0,50**

**R2O 9,00 ± 1,00**

**R2O3 16,00 ± 1,00**

### PHYSICAL FEATURES

Maximum humidity

0,00 %

Particle Size

**> 160 μm 1,00 ± 0,50**  
**> 90 μm 40,00 ± 5,00**  
**> 45 μm 50,00 ± 5,00**  
**< 45 μm 10,00 ± 3,00**

Coefficient of Expansion

54x10<sup>-7</sup>

Softening Point

820 °C

Presentation

Grit

### Use

Range T<sup>a</sup>

1000 - 1080 °C

Use

Exclusive use for ceramics