

TECHNICAL SPECIFICATIONS

IDENTIFICATION

Reference	Calcined Alumina A-45
Descriptions	Alumina

CHEMICAL COMPOSITION

Al ₂ O ₃	99,50
Surface BET (m ² /g)	0,60
PPC (20-1000°C)	0,4 max
α-Al ₂ O ₃	>97 %

PHYSICAL FEATURES

Maximum humidity	0,10
Presentation	D50 (μm) 45

RECOMMENDATIONS FOR USE

T ^a Maximum	1500 °C
Use	Ceramic