

TECHNICAL SPECIFICATIONS

IDENTIFICATION

Reference

PC-817

Descriptions

Kaolin

CHEMICAL COMPOSITION

SiO₂ 49,00 ± 1,00

Al₂O₃ 36,50 ± 0,50

CaO 0,1 ± 0,05

Fe₂O₃ 0,50 ± 0,05

K₂O 0,60 ± 0,30

TiO₂ 0,15 ± 0,05

P.C. 12,90

PHYSICAL FEATURES

Maximum humidity

4,00 ± 1,00

Presentation

Grain

RECOMMENDATIONS FOR USE

T^a Maximum

1500 °C

Use

Ceramic