

TECHNICAL SPECIFICATIONS

IDENTIFICATION

Reference

PC-818

Descriptions

Kaolin

CHEMICAL COMPOSITION

SiO₂ 53,50 ± 1,00

Al₂O₃ 32,50 ± 0,50

CaO 0,1 ± 0,05

Fe₂O₃ 0,50 ± 0,05

K₂O 0,60 ± 0,30

TiO₂ 0,15 ± 0,05

P.C. 12,80

PHYSICAL FEATURES

Maximum humidity

6,00 ± 1,00

Presentation

Grain

RECOMMENDATIONS FOR USE

T^a Maximum

1500 °C

Use

Ceramic