

TECHNICAL SPECIFICATION

Reference **PC - 847**

Description **Matt Grit**

CHEMICAL COMPOSITION

SiO ₂ 50,00 ± 1,50	RO 27,50 ± 1,00	R2O 4,50 ± 1,00
R2O3 18,00 ± 1,00		

PHYSICAL FEATURES

Maximum humidity **0,00 %**

Particle Size

> 207 μm	1,00 ± 0,50
> 45 μm	84,00 ± 5,00
< 45 μm	15,00 ± 5,00

Coefficient of Expansion **58x10⁻⁷**

Softening Point **1120°C**

Presentation **Grit**

Use

T^a Máxima **1160 - 1200 °C**

Use **Exclusive use for ceramics**

