

TECHNICAL SPECIFICATION

Reference

PC - 901

Description

Vetrosa Grit Low T^a

CHEMICAL COMPOSITION

| | | |
|-------------------------------|-----------------|-----------------|
| SiO ₂ 35,00 ± 1,50 | RO 11,00 ± 0,50 | R2O 2,00 ± 1,00 |
| R2O3 45,00 ± 1,00 | RO2 5,00 ± 0,50 | |
| | | |

PHYSICAL FEATURES

Maximum humidity

0,00 %

Particle Size

| | |
|----------|-------------|
| > 212 µm | 1,00 ± 0,50 |
| > 90 µm | 75,00 5,00 |
| > 45 µm | 20,00 5,00 |
| < 45 µm | 5,00 3,00 |

Coefficient of Expansion

58x10⁻⁷

Softening Point

840 °C

Presentation

Grit

Use

Range T^a

1020 - 1080 °C

Use

Exclusive use for ceramics